

Maximise Protection with Ranger Corrosion Guard (CG)


Ranger Corrosion Guard is an optional coating process that provides maximum environmental protection to our K-TORK range of valve actuators. When used in highly-corrosive environments, service life is vastly extended.

The K-TORK actuator is a true rotary actuator that does not require the conversion of linear motion to rotary motion. It provides a simple, highly accurate and reliable quarter-turn valve operation for on/off or modulating service.

The actuator's cast aluminium body and alloy steel vane are treated with a thermosetting tri-polymer resin coating system formulated for mechanical components requiring corrosion resistance and surface lubrication. Once applied, the system provides an armored layer of protection against a wide range of acids, caustics, alkalis, solvents and salt-laden environments.

The Ranger CG system can be provided on all K-TORK double-acting and spring-return models. Note that the K-TORK spring-return is totally sealed. The internals of the non-vented spring housing are never subject to compressed air, moisture or atmospheric contaminants.





K-TORK Ranger CG

Corrosion resistant treatment





K-TORK Ranger CG

Corrosion resistant treatment

K-TORK Ranger CG Coating Technical Data

The following estimates are guidelines only and are not intended for use in specifications.

Temperature range¹ -253 to +260 °C (-425 to +500 °F)

(intermittently to +370 °C (+700 °F)

Flexibility Unaffected by bend over 1/4"

> mandrel over complete temperature range

Taber abrasion 1,500 cycles for CS-17 wheel,

1,000 hours

Impact resistance Greater than 54 kg (120 lbf)

Pencil hardness 3 H (on coated grit-blasted surfaces)

(direct and reverse)

Boiling water Unaffected in 6 months

Unaffected in 1.000 hours Weathering

(accelerated)

Unaffected in 6 months Saturated salt spray

Greater than 1,000 volts/mil Dielectric strength

Electric conductance Non-conductive

Exterior durability 12 months

Adhesion Excellent

(cross hatch tape test ASTM D3359 method B)

1. This temperature range is applicable to the Ranger coating only. K-TORK actuators are available with the following operating temperature ranges:

Standard: -30 to +80 °C (-20 to +175 °F) High: -20 to +149 °C (0 to +300 °F) Low: -40 to +70 °C (-40 to +160 °F)

Steel and aluminum samples coated with the Ranger CG coating have remained immersed in the following chemicals for a period of 6 months with no deterioration:

Ethyl alcohol

Sec-butyl alcohol

Methyl isobutyl alcohol

Carbon chloride

Sodium hydroxide

Ammonium hydroxide (10%)

Hydrochloric acid (10%)

Phosphoric acid (85%)

Solid detergent (1%)

Calcium hypochloride (5%)

Sodium methoxide (40% methanol)

Isopropyl alcohol N-butyl alcohol

Hexylene glycol

Diethyl ether

Formaldehyde (30%)

Xylene

Linseed fatty acids

Hydrofluoric acid

Sodium chloride (25%)

Sodium hypochloride (5%)

Toluene

Diacetone alcohol

Glycerine

Methyl isobutyl ketone

Sulfuric acid (75%)

Nitric acid (10%)

Allyl chloride

Liquid detergent (100%)

Ferric chloride (5%)

Water

A full listing of our worldwide sales and service network is available on our website.

+44 (0)1225 733200 +44 (0)1225 333467

email mail@rotork.com

ControlsElectric Actuators and Control Systems

Fluid Systems
Fluid Power Actuato

r Actuators and Control Systems

Gears

Gearboxes and Gear Operators

Instruments

Site Services

Projects, Services and Retrofit

www.rotork.com

